

PARS PET-AMORPHOUS CHIPS		
موارد آزمایش	واحد	مقدار قابل قبول
Intrinsic Viscosity	dl/g	0.63± 0.03
DEG content	wt%	1.5≥
Color (CIE Lab)	L*	80≤
	b*	0.0≥
Carboxyl End Group	meq/kg	40≥
Melting point	C°	3 ± 249
Water content	wt%	0.3≥

Note: 1- Water Content determined before packing.

2- Color Determined after grinding.